

ACI Mix Design Example #2

- Consider the following example: The 28-day compressive strength should be 7,000 psi. The slump should be between 3 and 4 in. and the maximum aggregate size should not exceed ¾ in. The coarse and fine aggregates in the storage bins are wet.
- The properties of the materials are as follows:
 - Cement : Type I, specific gravity = 3.15
 - Coarse Aggregate: Bulk specific gravity (SSD) = 2.65; absorption capacity = 0.5%; dry-rodded unit weight = 100 lb./ft.³ surface moisture = 1%
 - Fine Aggregate: Bulk specific gravity (SSD) = 2.60; absorption capacity = 1.1%; fineness modulus = 2.70; surface moisture = 3.0%

Class ACI Mix Design Example

- **Step 1.** Required material information (already given).
- **Step 2.** The slump is given, consistent with Table 1.

Concrete construction	Slump, mm (in.)	
	Maximum*	Minimum
Reinforced foundation walls and footings	75 (3)	25 (1)
Plain footings, caissons, and substructure walls	75 (3)	25 (1)
Beams and reinforced walls	100 (4)	25 (1)
Building columns	100 (4)	25 (1)
Pavements and slabs	75 (3)	25 (1)
Mass concrete	75 (3)	25 (1)

- **Step 3.** Maximum aggregate size. Given: ¾ in.

Class ACI Mix Design Example

Step 4. Estimation of mixing water and air content. From Table 2, the recommended air content is 2.0%; the water requirement is 340 lb./yd.³.

Slump(in)	Maximum aggregate size (in.)							
	0.375	0.5	0.75	1	1.5	2	3	6
1 to 2	350	335	315	300	275	260	220	190
3 to 4	385	365	340	325	300	285	245	210
6 to 7	410	385	360	340	315	300	270	-
Air Content	3.0%	2.5%	2.0%	1.5%	1.0%	0.5%	0.3%	0.2%

Class ACI Mix Design Example

Step 5. Water/cement ratio. From Table 3, the estimate for required w/c ratio to give a 28-day strength of 7,000 psi is 0.33.

28-day Compressive Strength (psi)	Non-AE	AE
2,000	0.82	0.74
3,000	0.68	0.59
4,000	0.57	0.48
5,000	0.48	0.40
6,000	0.41	0.32
7,000	0.33	---

Class ACI Mix Design Example

- **Step 6.** Calculation of cement content. Based on steps 4 and 5, the required cement content is:

$$\text{weight of cement} = \frac{340 \text{ lb./yd.}^3}{0.33} = 1,030 \text{ lb./yd.}^3$$

Class ACI Mix Design Example

Step 7. Estimation of coarse aggregate content. Interpolating Table 4 for the fineness modulus of the fine aggregate of 2.70

Max Aggregate (in.)	Fineness Modulus						
	2.4	2.5	2.6	2.7	2.8	2.9	3
0.375	0.50	0.49	0.48	0.47	0.46	0.45	0.44
0.500	0.59	0.58	0.57	0.56	0.55	0.54	0.53
0.750	0.66	0.65	0.64	0.63	0.62	0.61	0.60
1.000	0.71	0.70	0.69	0.68	0.67	0.66	0.65
1.500	0.75	0.74	0.73	0.72	0.71	0.70	0.69
2.000	0.78	0.77	0.76	0.75	0.74	0.73	0.72
3.000	0.82	0.81	0.80	0.79	0.78	0.77	0.76
6.000	0.87	0.86	0.85	0.84	0.83	0.82	0.81

Class ACI Mix Design Example

- The coarse aggregate will occupy:

$$0.63 \times 27 \text{ ft.}^3 / \text{yd.}^3 = 17.01 \text{ ft.}^3 / \text{yd.}^3$$

Value from
Table 4

- The OD weight of the coarse aggregate

$$17.01 \text{ ft.}^3 / \text{yd.}^3 \times 100 \text{ lb.} / \text{ft.}^3 = 1,701 \text{ lb.} / \text{yd.}^3$$

Dry-Rodded
Unit Weight

Class ACI Mix Design Example

- **Step 8.** Estimation of fine aggregate content by the absolute volume method.

➤ Water: $340 \text{ lb.} / 62.4 \text{ lb.} / \text{ft.}^3 = 5.45 \text{ ft.}^3$

➤ Cement: $1,030 \text{ lb.} / (3.15 \times 62.4 \text{ lb.} / \text{ft.}^3) = 5.24 \text{ ft.}^3$

➤ Coarse Aggregate: $1,701 \text{ lb.} / (2.65 \times 62.4 \text{ lb.} / \text{ft.}^3) = 10.29 \text{ ft.}^3$

➤ Air: $2.0\% \times 27 \text{ ft.}^3 / \text{yd.}^3 = 0.54 \text{ ft.}^3$

Total

21.52 ft.³

Class ACI Mix Design Example

- Therefore, the fine aggregate must occupy a volume of:

$$27 \text{ ft.}^3 - 21.54 \text{ ft.}^3 = 5.48 \text{ ft.}^3$$

- The SSD weight of the fine aggregate is:

$$5.48 \text{ ft.}^3 \times 2.60 \times 62.4 \text{ lb.} / \text{ft.}^3 = 889 \text{ lb.}$$

Specific Gravity
of Fine Aggregate

Unit Weight
of Water

Class ACI Mix Design Example

- **Step 9.** Adjustment for moisture in the aggregate.

The weight of aggregate from the stock pile is:

$$Weight_{Stock\ Pile} = Weight_{OD} (1 + MC)$$

The change in the weight water due to the moisture of the aggregate from the stock pile is:

$$\Delta Weight_{Water} = Weight_{OD} (SM)$$

$$Adjusted\ Weight_{Water} = Weight_{Water} - \Delta Weight_{Water}$$

Class ACI Mix Design Example

- **Step 9.** Compute stockpile weight based on moisture content

- Fine aggregate required from the stockpile is:

$$889 \text{ lb.} (1 + 0.041) = 925 \text{ lb.} / \text{yd.}^3$$

Moisture Content 4.1%

- Coarse aggregate required from the stockpile is:

$$1,701 \text{ lb.} (1 + 0.015) = 1,727 \text{ lb.} / \text{yd.}^3$$

Moisture Content 1.5%

Class ACI Mix Design Example

- **Step 9.** Adjust the amount of water based on moisture content

The required mixing water required is:

$$340 \text{ lb.} - 889 \text{ lb.} (0.03) \leftarrow \text{fine aggregate}$$

Surface moisture 3.0%

$$- 1,701 \text{ lb.} (0.01) \leftarrow \text{coarse aggregate}$$

$$= 296 \text{ lb.} / \text{yd.}^3$$

Surface moisture 1%

Class ACI Mix Design Example

➤ Thus the estimated batch weights per yd^3 are:

Water	=	296 lb.
Cement	=	1,030 lb.
Coarse aggregate (wet)	=	1,727 lb.
Fine aggregate (wet)	=	925 lb.

Total	=	3,978 lb./yd.³
	=	147.3 lb./ft.³